

Fritzøe Engros AS  
Postboks 2055 Stubberød  
3255 Larvik  
Norge

## Classification of reaction to fire in accordance with EN 13501-1

### 1 Introduction

This classification report defines the classification assigned to “Fritzøe MAGboard” in accordance with the procedure given in EN 13501-1:2018.

### 2 Details of classified product

#### 2.1 General

The product “Fritzøe MAGboard” is defined as a non-combustible board. Its classification is valid for the following end use application: building board.

#### 2.2 Product description

The product, “Fritzøe MAGboard”, is fully described below.

According to the client: Product called “Fritzøe MAGboard”, described below:

Product	Content (%)		Thickness (mm)	Density (kg/m <sup>3</sup> )	Organic content (%)	Colour
Fritzøe MAGboard	Mgo	50.6	6	1000 – 1200	14.3	White
	Mgcl2	27.0				
	Perlite	3.1				
	Chip	14.3				
	Filler	5.0				

### 3 Reports and results in support of this classification

#### 3.1 Test reports

Table 1 Test reports forming the basis for this classification.

Name of laboratory	Name of sponsor	Test report reference no	Accredited test methods and date
RISE	Fritzøe Engros AS	O100609-1150004	EN ISO 1182:2020
RISE	Fritzøe Engros AS	O100609-1150004-02	EN ISO 1716:2010

#### RISE Research Institutes of Sweden AB

Postal address  
Box 857  
501 15 BORÅS  
SWEDEN

Office location  
Brinellgatan 4  
504 62 Borås  
SWEDEN

Phone / Fax / E-mail  
+46 10-516 50 00  
+46 33-13 55 02  
info@ri.se

Confidentiality level

C2 - Internal

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

**3.2 Test results**

Table 2 Test results showing the worst case as found in the test program performed.

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN ISO 1182		5		
	$\Delta T$ (°C)		8	Compliant
	$\Delta m$ (%)		48	Compliant
	$t_f$ (s)		0	Compliant
EN ISO 1716		3		
	PCS (MJ/kg)* (4)		0.8	Compliant

\* : the product is homogeneous

(4): the parameter for the product as a whole

**4 Classification and field of application**

**4.1 Reference of classification**

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2018.

**4.2 Classification**

The product called “Fritzøe MAGboard” in relation to its reaction to fire behaviour is classified:

A1

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

<b>Fire Behaviour</b>
<b>A1</b>

**Reaction to fire classification: *A1***

#### 4.3 Field of application:

This classification is valid for the following product parameters:

Product specification, as specified in 2.2 in this report

Nominal density: 1000 – 1200 kg/m<sup>3</sup>.

Nominal organic content: 14.3 %.

The sample was delivered by the client. RISE, Fire and Safety was not involved in the sampling procedure.

#### 5 Limitations

This classification document does not represent type approval or certification of the product.

### RISE Research Institutes of Sweden AB Fire and safety - Reaction to Fire Medium Scale Lab

Performed by



Susanne Blomqvist

Examined by



Per Thureson

# Verification

Transaction 09222115557483024216

## Document

O100609-1150004-1 EN 13501-1

Main document

3 pages

*Initiated on 2022-12-08 09:42:51 CET (+0100) by Susanne Blomqvist (SB)*

*Finalised on 2022-12-08 11:02:15 CET (+0100)*

## Signing parties

Susanne Blomqvist (SB)

RISE Research Institutes of Sweden AB

Company reg. no. 556464-6874

*susanne.blomqvist@ri.se*



*Signed 2022-12-08 09:44:08 CET (+0100)*

Per Thureson (PT)

RISE Reserach Institutes of Sweden AB

*per.thureson@ri.se*



*Signed 2022-12-08 11:02:15 CET (+0100)*

This verification was issued by Scrive. Information in italics has been safely verified by Scrive. For more information/evidence about this document see the concealed attachments. Use a PDF-reader such as Adobe Reader that can show concealed attachments to view the attachments. Please observe that if the document is printed, the integrity of such printed copy cannot be verified as per the below and that a basic print-out lacks the contents of the concealed attachments. The digital signature (electronic seal) ensures that the integrity of this document, including the concealed attachments, can be proven mathematically and independently of Scrive. For your convenience Scrive also provides a service that enables you to automatically verify the document's integrity at: <https://scrive.com/verify>

